

ISO-9001 Registered Quality System. ISO-21469 Compliant.

Sales, Service & Distribution Center

Newark, NJ 07105

Phone: 973-589-9150 Fax: 973-589-4432

Manufacturing, Sales, Service & Distribution Center

Toledo, OH 43605

Phone: 419-691-2491 Fax: 419-693-3806

Sales and Tech Service Support

Phone: 1-800-733-4755

PRODUCT DATA

LUBRIPLATE CHAIN & CABLE FLUID

INDUSTRIAL STRENGTH PENETRATING FLUID

DESCRIPTION

LUBRIPLATE Chain & Cable Fluid is a lubricating, penetrating and cleansing fluid designed for a multitude of applications. It penetrates the strands to lubricate and reduce friction between wire rope strands, and to lubricate and protect the inner core from rust and corrosion. The same basic principles also apply to the lubrication of roller chains. It provides the required penetration, cleansing and lubrication of the inside of the links is vital in addition to the outside protection and lubrication. LUBRIPLATE Chain & Cable Fluid performs all of these functions most successfully.

APPLICATIONS

Wire rope on shipyard Gantry cranes – exposed to very severe service, salt air, and salt water.

General-purpose lubricant for application on vending and sewing machines.

Speedometer cable and housing - penetrates, creeps and softens grease as well as lubricates.

Control cables, latches, pins etc., on concrete trucks penetrates concrete and frees metal parts.

Door Locks - Frees frozen door locks.

Nut Busting, prevents rusting.

Penetrates and lubricates equipment components exposed to adverse conditions; salt, road grime, rust and corrosion, plus many other contaminants

ADVANTAGES

- ⇒ Will not produce a dry surface; it will maintain a moist film.
- ⇒ This unique film will not pick up dust and dirt, but rather acts as a cleansing agent.

Typical Test Data

PROPERTY	TEST METHOD	TYPICAL RESULTS*
Viscosity SUS @ 100°F	ASTM D-2161	150
Viscosity cSt @ 40°C	ASTM D-445	32
Viscosity SUS @ 210°F	ASTM D-2161	45
Viscosity cSt @ 100°C	ASTM D-445	6
ISO Grade	ASTM D-2422	32
SAE Grade		10
Flash Point	ASTM D-92	310°F/154°C
Fire Point	ASTM D-92	350°F/177°C
Pour Point	ASTM D-97	-40°F/-40°C
Color	ASTM D-1500	L-4.0
API Gravity	ASTM D-287	23.0

Part No.
L0135-007
L0135-013
L0135-035
L0135-039
L0135-040
L0135-063

