



ISO-9001 Registered Quality System.  
ISO-21469 Compliant.

### Sales, Service & Distribution Center

Newark, NJ 07105

Phone: 973-589-9150 Fax: 973-589-4432

### Manufacturing, Sales, Service & Distribution Center

Toledo, OH 43605

Phone: 419-691-2491 Fax: 419-693-3806

### Sales and Tech Service Support

Phone: 1-800-733-4755

## PRODUCT DATA

# LUBRIPLATE "1500" SERIES

## DESCRIPTION & ADVANTAGES

**LUBRIPLATE No. 1500, 1550, 1551, and 1552** are lithium complex greases that can be used for a variety of industrial, automotive and heavy-duty construction applications. These rugged, extreme pressure lubricants can withstand higher operating temperatures than traditional lithium multi-purpose greases as well as most lithium complex greases.

**LUBRIPLATE No. 1552 and No. 1551** are tacky, adhesive and very water resistant. The film strength and shear stability of these products are exceptional resulting in wear reduction and long lubricant life.

## APPLICATIONS

**LUBRIPLATE No. 1500** can be used for a variety of industrial and automotive applications. It is ideally suited for use in leaky gear cases that require a semi-fluid grease. It is also recommended for use in new on-highway trailer wheel bearings where a semi-fluid grease is required. LUBRIPLATE No. 1500 can also be used in centralized lubrication systems, especially those operating at higher temperatures.

**LUBRIPLATE No. 1550** is ideal for heavy load, tight tolerance situations and can be pumped easily through automatic dispensing systems on construction and mining equipment as well as industrial applications.

**LUBRIPLATE No. 1552 and No. 1551** provide outstanding lubrication in a variety of applications including:

- ⇒ Automotive (including the fleet and truck operator)
- ⇒ Marine
- ⇒ Construction
- ⇒ Logging
- ⇒ Mining
- ⇒ Industrial



## Typical Test Data

PROPERTY	TEST METHOD	TYPICAL RESULTS*			
		No 1552	No 1551	No 1550	No 1500
NLGI No.		2	1	0	00
Dropping Point	D-566	500°F+	470°F	451°F	N/A
Viscosity: SUS @ 100°F	D-2161	1100	1100	1100	1100
cSt @ 40°C	D-445	215	215	215	215
SUS @ 210°F	D-2161	92	92	92	92
cSt @ 100°C	D-445	18	18	18	18
Flash Point, °F/°C	D-92	500/260	500/260	500/260	500/260
Fire Point, °F/°C	D-92	545/285	545/285	545/285	545/285
Specific Gravity	D-4052	0.96	0.9485	0.9018	0.90
Timken E.P. Test OK Load	D-2783	60 lbs.	50 lbs.	50 lbs.	50 lbs.
Four Ball E.P. Test OK Load	D-2783	680 kg.	480 kg.	460 kg.	420 kg.
Four Ball Wear Test	D-2266	.45 mm	.45 mm	.45 mm	.54 mm
Texture		Tacky	Tacky	Tacky	Tacky
Oil Separation	D-1742	1.1%	5.0%	N/A	N/A
Evaporation Loss	D-972	0.24%	0.24%	0.24%	0.24%
Oxidation Stability	D-942	2 lbs.	2lbs.	2lbs.	2.5 lbs.
Corrosion: 3 hours	D-130	1a	1a	1a	1a
Water Washout	D-1264	2.75%	2.25%	N/A	N/A
Wheel Bearing Leakage	D-1263	5.5 gm.	5.5 gm.	N/A	N/A

### PACKAGING AVAILABLE

35 lb. Pail  
120 lb. Quarter Size Drum  
420 lb. Full Size Drum  
Carton, 40/14 oz. Cartridges  
Carton, 40/14.5 oz. Cartridges

### PACKAGING AVAILABLE

Carton, 4/7 lb. Jugs  
Carton, 12/2 lb. Bottles  
35 lb. Pail  
120 lb. Quarter Size Drum  
420 lb. Full Size Drum

### No. 1552

L0166-035  
L0166-039  
L0166-040  
\*\*\*  
L0166-098

### No. 1550

\*\*\*  
\*\*\*  
L0164-035  
L0164-039  
L0164-040

### No. 1551

L0165-035  
L0165-039  
L0165-040  
L0165-098  
\*\*\*

### No. 1500

L0163-007  
L0163-013  
L0163-035  
L0163-039  
L0163-040