MALLEABLE IRON FITTINGS



Class 300 (XS/XH)

FIGURE 1160		Ci-	••				,	Unit V	/eight
45° Street Elbow		Size		С		K		Black	
		NPS	DN	in	mm	in	mm	lbs	kg
		1/2	15	1	25	13/8	35	0.36	0.16
		3/4	20	11//8	29	1 %16	40	0.54	0.24
		1	25	1 5⁄16	33	1 ¹³ ⁄16	47	0.85	0.39
		11/4	32	1½	38	21/8	54	1.50	0.68
		11/2	40	1 ¹¹ ⁄ ₁₆	43	2 ⁵ ⁄16	59	2.06	0.93
MOG	<u> </u>	2	50	2	51	2 ¹¹ / ₁₆	68	3.34	1.51

FIGURE 1162		Size		С		Unit Weight			
45° Elbow						Black		Galv.	
		NPS	DN	in	mm	lbs	kg	lbs	kg
		1/4	8	¹³ / ₁₆	22	0.19	0.09	0.19	0.09
		3/8	10	7/8	22	0.28	0.13	0.28	0.13
		1/2	15	1	25	0.43	0.20	0.43	0.20
		3/4	20	1½	29	0.66	0.30	0.66	0.30
		1	25	1 5⁄16	33	1.00	0.45	1.00	0.45
1 286		11/4	32	11/2	38	1.67	0.76	1.67	0.76
26		11/2	40	1 ¹¹ / ₁₆	43	2.15	0.98	2.15	0.98
	Ç	2	50	2	51	3.40	1.54	3.40	1.54
(1)	*	21/2	65	21/4	57	5.51	2.50	5.51	2.50
		3	80	2 ½	64	8.10	3.67	8.10	3.67
		4	100	2 ¹³ / ₁₆	73	13.41	6.08	13.41	6.08

Note: See following page for pressure-temperature ratings. Galvanized weights may vary. Please contact your Anvil Representative if you need verification. All Elbows & Tees 3/s" (10 DN) and Larger are 100% Gas Tested at a Minimum of 100 PSI. (6.9 bar)

PROJECT INFORMATION	APPROVAL STAMP
Project:	☐ Approved
Address:	Approved as noted
Contractor:	☐ Not approved
Engineer:	Remarks:
Submittal Date:	
Notes 1:	
Notes 2:	

MALLEABLE IRON FITTINGS





Malleable Iron Threaded Pipe Unions Pressure - Temperature Ratings Pressure Temperature Class 150 Class 250 Class 300 (°F) (°C) psi bar psi -28.9° -20° 300 20.7 500 34.5 600 41.4 to to 150° 65.6° 200° 93.3° 18.3 31.4 550 37.9 265 455 15.5 250° 121.1° 225 405 27.9 505 34.8 300° 148.9° 185 12.8 360 24.8 460 31.7 350° 176.7° 150 10.3 315 21.7 415 28.6 400° 204.4° 110 7.6 270 18.6 370 25.5 232.2° 325 450° 75 5.2 225 15.5 22.4 500° 260.0° 180 12.4 280 19.3 550° 287.8° 130 9.0 230 15.9

Note: Unions with Copper or Copper Alloy seats are not intended for use where temperature exceeds 450°F





For Listings/Approval Details and Limitations, visit our website at www.anvilintl.com or contact an Anvil Sales Representative.

Malleable Iron Threaded Fittings											
Pressure - Temperature Ratings											
				Pres	ssure						
Temperature		01 4=0		Class 300							
		Class 150		Sizes 1/4"-1"		Sizes 11/4"-2"		Sizes 2½"-3"			
(°F)	(°C)			(6–25 mm) psi bar		(32–51 mm) psi bar		(64–76 mm) psi bar			
-20° to 150°	-28.9° to 65.6°		20.7	2,000	137.9	1,500	103.4	1,000	68.9		
200°	93.3	265	18.3	1,785	123.1	1,350	93.1	910	62.7		
250°	121.1	225	15.5	1,575	108.6	1,200	82.7	825	56.9		
300°	148.9	185	12.8	1,360	93.8	1,050	72.4	735	50.7		
350°	176.7	150	10.3	1,150	79.3	900	62.1	650	44.8		
400°	204.4	_	_	935	64.5	750	51.7	560	38.6		
450°	232.2	ı	-	725	50.0	600	41.4	475	32.8		
500°	260.0	_	_	510	35.2	450	31.0	385	26.5		
550°	287.8	_	_	300	20.7	300	20.7	300	20.7		

Anvil Class 150/300 Malleable Iron Fittings conform to ASME B16.3 and Unions conform to ASME B16.39.

ALL ELBOWS & TEES %" (10 DN) and LARGER ARE 100% GAS TESTED AT A MINIMUM OF 100 PSI. (6.9 bar)

Standards and Specifications									
	Dimensions	Material	Galvanizing*	Thread	Pressure Rating				
MALLEABLE IRON FITTINGS									
Class 150/PN 20	ASME B16.3	ASTM A-197	ASTM A-153	ASME B1 20.1	ASME B16.3				
Class 300/PN 50	ASME B16.3	ASTM A-197	ASTM A-153	ASME B1 20.1	ASME B16.3				
MALLEABLE IRON UNIONS									
Class 150/PN 20	ASME B16.39	ASTM A-197	ASTM A-153	ASME B1 20.1	ASME B16.39				
Class 250	ASME B16.39	ASTM A-197	ASTM A-153	ASME B1 20.1	ASME B16.39				
Class 300/PN 50	ASME B16.39	ASTM A-197	ASTM A-153	ASME B1 20.1	ASME B16.39				

^{*} ASTM B 633. Type I, SC 4, may be supplied as alternate zinc coating per applicable ASME B16 product standard.

MALLEABLE IRON FITTINGS



General Assembly of Threaded Fittings

- 1) Inspect both male and female components prior to assembly.
 - Threads should be free from mechanical damage, dirt, chips and excess cutting oil.
 - Clean or replace components as necessary.
- 2) Application of thread sealant
 - Use a thread sealant that is fast drying, sets-up to a semi hard condition and is vibration resistant. Alternately, an anaerobic sealant may be utilized.
 - Thoroughly mix the thread sealant prior to application.
 - Apply a thick even coat to the male threads only. Best application is achieved with a brush stiff enough to force sealant down
 to the root of the threads.
- 3) Joint Makeup
 - For sizes up to and including 2" pipe, wrench tight makeup is considered three full turns past handtight. Handtight engagement for 1/2" through 2" thread varies from 41/2 turns to 5 turns.
 - For $2^{1}/2^{1}$ through 4" sizes, wrench tight makeup is considered two full turns past handtight. Handtight engagement for $2^{1}/2^{1}$ through 4" thread varies from $5^{1}/2$ turns to $6^{3}/4$ turns.