

**RUST-OLEUM®**

## HS9300 SYSTEM EPOXY PRIMER

### DESCRIPTION AND USES

The HS9300 System Epoxy Primer is a two-component, low VOC polyamine converted epoxy primer. Designed as primers for clean, abrasive-blasted or slightly rusted steel, masonry or concrete for topcoating with 9400 System High Gloss Polyester Urethane or 9700 250 VOC Acrylic Polyester Urethane.

### PRODUCTS

SKU	Description
HS9369	Flat Red
HS9381	Flat Gray
HS9303604	Activator

### RECOMMENDED TOPCOATS

9400 System High Gloss Polyester Urethane  
9700 System 250 VOC Acrylic Polyester Urethane

### PRODUCT APPLICATION

#### SURFACE PREPARATION

**ALL SURFACES:** Remove all dirt, grease, oil, salt or other contaminants by washing surface with 3599 Industrial Pure Strength® Cleaner/Degreaser, commercial detergent or other suitable cleaner. Rinse thoroughly with fresh water and allow to fully dry. Thoroughly cured previous coatings or new metal surfaces which are very smooth may require scuff sanding to maximize adhesion.

**STEEL – SEVERE EXPOSURES:** Abrasive blast to a minimum SSPC-SP-6 Commercial Grade (NACE 3). Two coats of primer must be used.

**STEEL – MODERATE EXPOSURES:** Scrape and wire brush or power tool clean to remove loose rust, scale and deteriorated previous coatings.

**CONCRETE AND MASONRY SURFACES:** After cleaning, repair surface defects and remove deteriorated previous coatings. Abrasive blast or acid etch smooth dense concrete using 108 Cleaning & Etching Solution followed by thoroughly rinsing with fresh water. Allow new concrete and masonry to cure at least 30 days before coating. Any concrete surface must be protected from moisture transmission from uncoated areas.

### PRODUCT APPLICATION (cont.)

#### APPLICATION

Mix the base component well before adding HS9303 Activator. Continue to mix while adding activator. Allow a 30 minute induction period before using. The container is short-filled to allow for addition of activator. Do not activate more material than can be used in an 8 hour period. Apply only when air and surface temperatures are between 60-100°F (16-38°C) and surface is at least 5° above dew point.

#### EQUIPMENT RECOMMENDATIONS

(Comparable equipment also suitable).

**BRUSH:** Natural or synthetic bristle recommended.

**ROLLER:** Epoxy compatible lamb's wool or synthetic cover recommended.

**AIR-ATOMIZED SPRAY:**

Method	Fluid Tip	Fluid Delivery	Atomization
Pressure	0.055-.070	16 oz./min.	25-60 psi
Siphon	0.055-.070	—	25-60 psi

**AIRLESS SPRAY:**

Fluid Pressure	Fluid Tip	Filter Mesh
1,800-2,400 psi	0.017-0.021	60

#### THINNING

**BRUSH/ROLLER:** Normally not required. 333 Thinner not recommended.

**AIR-ATOMIZED SPRAY:** 333 Thinner: Use 15-20% or as needed (approximately 1.5 pints per gallon).

**AIRLESS SPRAY:** 333 Thinner: Normally not required: Use 5-10% if needed (approximately 1.5 pints per gallon).

#### CLEAN-UP

333 Thinner or Acetone.

**NOTE:** Use 333 Thinner to maintain VOC compliance. Use 160 Thinner where VOC compliance is not required. 333 Thinner will lower the flashpoint of coatings to which it is added.



## TECHNICAL DATA

# HS9300 SYSTEM EPOXY PRIMER

### PHYSICAL PROPERTIES

<b>Resin Type</b>		Polyamine Converted Epoxy
<b>Pigment Type</b>		Calcium Borosilicate, Brown Iron Oxide, Black Iron Oxide, Titanium Dioxide, Magnesium Silicate
<b>Solvents</b>		Xylene, Propylene Glycol Methyl Ether
<b>Weight*</b>	<b>Per Gallon</b>	12.0-12.5 lbs.
	<b>Per Liter</b>	1.44-1.50 kg
<b>Solids*</b>	<b>By Weight</b>	72%
	<b>By Volume</b>	53%
<b>Volatile Organic Compounds*</b>		HS9369: 403 g/l (3.36 lbs./gal.) HS9381: 398 g/l (3.31 lbs./gal.)
<b>Recommended Dry Film Thickness (DFT) Per Coat</b>		1.5-2.5 mils (37.5-62.5µ)
<b>Wet Film to Achieve DFT (unthinned material)</b>		3-5 mils (75-125µ)
<b>Theoretical Coverage at 1 mil DFT (25µ)</b>		835 sq. ft./gal. (19.9 m <sup>2</sup> /l)
<b>Practical Coverage at Recommended DFT (assumes 15% material loss)</b>		275-475 sq. ft./gal. (6.5-11.3 m <sup>2</sup> /l)
<b>Mixing Ratio</b>		7:1 Base to activator by volume (HS9303 activator)
<b>Induction Period</b>		30 minutes
<b>Pot Life at 70-80°F (21-27°C)</b>		8-16 hours
<b>Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity</b>	<b>Tack-free</b>	1-2 hours
	<b>Handle</b>	3-4 hours
	<b>Recoat</b>	Anytime after 1 hour
<b>Force Cure</b>		10 minutes at 225°F (107°C) (dry to handle after cooling)
<b>Dry Heat Resistance</b>		300°F (149°C)
<b>Shelf Life</b>		5 years
<b>Safety Information</b>		<b>CONTAINS XYLENE, PROPYLENE GLYCOL METHYL ETHER AND EPOXY AND POLYAMINE RESINS. WARNING! FLAMMABLE LIQUID AND VAPOR. HARMFUL IF INHALED MAY AFFECT BRAIN OR NERVOUS SYSTEM CAUSING DIZZINESS, HEADACHE OR NAUSEA. CAUSES RESPIRATORY TRACT, EYE AND SKIN IRRITATION. MAY CAUSE ALLERGIC SKIN REACTION. FOR INDUSTRIAL OR COMMERCIAL USE ONLY. KEEP OUT OF REACH OF CHILDREN. SEE THE PRODUCT SAFETY DATA SHEET (SDS) AND LABEL WARNINGS FOR ADDITIONAL SAFETY INFORMATION</b>

\* Activated material

Calculated values are shown and may vary slightly from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.



Rust-Oleum Corporation  
11 Hawthorn Parkway  
Vernon Hills, Illinois 60061  
An RPM Company

Phone: 877-385-8155  
[www.rustoleum.com/industrial](http://www.rustoleum.com/industrial)

Form: GDH-893  
Rev.: 121415