

RUST-OLEUM®

MEDICI® DECORATIVE POLYUREA FLOOR COATING

DESCRIPTION AND USES

The Medici® Decorative Polyurea Floor Coating is a high gloss, UV stable aliphatic polyurea floor coating for use in industrial and commercial facilities. It combines two different finish colors in a simultaneous roller application to obtain a faux stain finish. It is suitable for both interior and exterior applications.

PRODUCTS

280938	Sierra Sunset
280947	Terra Cotta
280939	Brown Slate
280950	Stone

RECOMMENDED PRIMER

Medici can be applied direct to properly prepared concrete or used over one of the following primers. If there is a moisture issue with the floor, then it must be primed with one of the TVB Primers.

- S6511 Penetrating Prime & Seal Primer
- TVB Water Based Topside Vapor Barrier
- TVB 100% Solids Topside Vapor Barrier
- TurboPrime™
- ECO Prime™

PACKAGING

Each Medici finish is packaged in a kit containing 90 fl. oz. of coating in a flexible pouch and two 8 fl. oz. containers of Stabilizer/Tint additives. Each container of Stabilizer/Tint produces a different color.

APPEARANCE

High Gloss

PRODUCT APPLICATION

SURFACE PREPARATION

The concrete surface must be free of all dirt, grease, oil, fats, and other contamination. Remove surface contamination by cleaning with Krud Kutter® Cleaner Degreaser, detergent, or other suitable cleaner. Rinse thoroughly with clean, fresh water and allowed to dry.

Note: The substrate must be completely dry prior to application of Medici. Polyurea coatings are sensitive to moisture and can affect proper curing of the coating.

NEW, UNCOATED CONCRETE: New concrete must be allowed to cure for a minimum of 30 days before application. In addition to the aforementioned cleaning, the concrete must be further prepared by mechanical grinding or acid etch to remove all laitance and produce a suitable surface profile.

PREVIOUSLY COATED CONCRETE: Previously coated concrete must be in good sound condition with the existing coating tightly adhering to the concrete. In addition to the aforementioned cleaning the existing coating must be sanded to dull the finish and produce a slight surface profile. Remove all sanding dust by vacuum. Do not wipe the floor with denatured alcohol or other solvent. If wiping is necessary, use only urethane grade Methyl Ethyl Ketone (MEK).

PRODUCT APPLICATION (cont.)

CONCRETE REPAIR

All spalls and cracks must be chased out and repaired to ICRI standards using an appropriate Concrete Saver patching material.

MIXING

Both components should be pre-conditioned to a minimum of 50°F (10°C) prior to use. Be sure the air and surface temperatures are at least 5° above the dew point. The Medici finish is moisture sensitive, so be sure the outside of the flexible pouch is dry and free of condensation.

Cut off the top of the flexible pouch and divide the material equally into two separate clean pails; 45 fl.oz. in each pail. Add the entire contents of the Stabilizer/Tint into each of the pails and power mix for 2-3 minutes at 500-700 rpm.

APPLICATION

Apply only when air, material and floor temperatures are between 50-90°F (10-32°C). Do not apply in direct sunlight or when temperature is rising.

The coating is applied using a special Medici® Roller and Medici Roller Pan. Fill each side of the Medici Roller Pan with the different colors.

It is strongly suggested that the Medici Roller be de-linted before use. Use duct tape, but rather than wrapping the duct tape around the roller, wrap a piece of duct tape around your hand, sticky side out, and lightly dab or sweep the roller to pick up and remove loose fibers.

The faux stain affect of Medici finish is achieved by the dual roller application with two colors. The colors will blend and overlay each other in a way which is unique for each application and is very applicator dependant.

If more than one applicator is going to be involved with the application of the coating, then they should not stay in just one location, but move around the area to reduce the appearance of patterns developing in the finish. Have an application plan determined before beginning application. Be sure to have enough material mixed prior to beginning. Having an excess would be best. Each applicator must wear clean, sharp spikes while applying the coating.

Lightly saturate the Medici Roller with the two colors in the roller pan. Do not push down on the roller as this will cause it to thicken up and reduce the texture that can be achieved. Get enough material on the roller to fully color each side. Each load of the roller should provide enough material to cover a 5x5 foot area (25 sq. ft.). So keep this in mind as you begin the application. Start the application by rolling out a 3x3 foot 'W' pattern and a 3x3 foot 'M' pattern adjacent to it. Use light application force on the roller. Once the 'W' and 'M' patterns are down, rotate your position 90° and roll in the opposite direction spreading the coating out and filling in the area. Continue to 'walk in circles' while spreading the coating lightly with the roller.

Once the 5x5 foot area is completed, re-load the roller and repeat the procedure for another 5x5 foot area adjacent to the previous area.



TECHNICAL DATA

MEDICI

PRODUCT APPLICATION (cont.)

Begin in the center of the new area and spread out the coating blending it back into the previous area. Maintain the same coverage rate for each section to ensure a uniform appearance. Repeat the process until the entire floor is coated.

It is strongly suggested the Medici Roller is changed out after an hour of use, otherwise the nap can begin to stiffen and this can affect the appearance of the application. Cut in along walls and other areas with a 3" chip brush blending the colors to achieve the same appearance.

Allow the coating to dry for at least 4 hours before applying a clear finish.

If slip resistance is desired, apply a clear finish coat of FastKote® UV with the durability Additive.

THINNING

None required.

CLEAN-UP

Methyl Ethyl Ketone (MEK)

EQUIPMENT RECOMMENDATIONS

ROLLER: Use Medici Roller and Roller Pan only.

BRUSH: Use a disposable natural fiber chip brush, 2-4 inch wide for cut in work.

PERFORMANCE CHARACTERISTICS

Tensile Strength (ASTM D412)	5,500
Compressive Strength (ASTM D695)	12,000
Elongation (ASTM D412)	75
Hardness, Shore D (ASTM D2240)	84
Gloss (ASTM D523) @ 60°	91+
Abrasion Resistance (ASTM D4060) CS-17 Wheel, 1,000 g load, 1,000 cycles	43



TECHNICAL DATA

MEDICI

PHYSICAL PROPERTIES

Resin Type		Aliphatic Polyurea
Weight	Per Gallon	10.0 lbs/gal - Clear (finish colors are slightly higher and varies with color)
	Per Liter	1.2 kg/l - Clear (finish colors are slightly higher and varies with color)
Solids by Volume		90%
Volatile Organic Compounds**		<50 g/l**
Practical Coverage Rate		400 sq. ft./gal. Coverage rate can vary depending on the texture and porosity of the concrete
Dry Times @ 72° F and 50% Relative Humidity†	Recoat	4-12 hours*
	Light traffic	3-6 hours
	Full traffic	24 hours
Shelf Life		18 months unopened 6 months once the Stabilizer/Tint has been added
Safety Information		See SDS

Calculated values are shown and may vary slightly from the actual manufactured material.

† Dry times will be increase if temperatures are less than 65° F (18°C) and/or the Relative Humidity is less than 50%.

* If 12 hour recoat time has elapsed, the coating must be sanded prior to recoating.

** Calculated Applied VOC

CHEMICAL RESISTANCE

Acetic Acid 100%	RC	Methanol	R	Sugar/H2O	R
Acetone	R	Methylene Chloride	C	Sulfuric Acid 10%	R
Ammonium Hydroxide 50%	RC	Mineral Spirits	R	Sulfuric Acid >50%	R
Benzene	RC	Motor Oil	R	Toluene	R
Brake Fluid	R	MTBE	C	1, 1,1-Trichlorethane	C
Brine saturated H2O	R	Muriatic Acid 10%	R	Trisodium Phosphate	R
Chlorinated H2O	R	NaCl/H2O 10%	R	Vinegar/H2O 5%	R
Diesel fuel	R	Nitric Acid 20%	RC	H2O 14 days at 82° C	R
Ethanol	R	Phosphoric Acid 10%	R	Xylene	NR
Gasoline	R	Phosphoric Acid 50%	NR		
Gasoline/5% MTBE	R	Potassium Hydroxide 10%	R		
Gasoline/5% Methanol	R	Potassium Hydroxide 20%	R, Dis		
Hydrochloric Acid 20%	R	Propylene Carbonate	RC		
Hydrofluoric Acid 10%	RC	Skydrol	RC		
Hydraulic fluid (oil)	R	Sodium Hydroxide 25%	R		
Isopropyl Alcohol	R	Sodium Hydroxide 50%	R, Dis		
Jet Fuel (JP-4)	R	Sodium Hypochlorite 10%	RC		
Lactic Acid	RC	Sodium Bicarbonate	R		
MEK	NR	Stearic Acid	R		

Chemical Resistance Key

R=recommended/little or no visible damage
 RC=recommended conditional/some effect, swelling or discoloration
 C=Conditional/Cracking-wash within one hour of spillage to avoid effects
 NR=Not recommended
 Dis=Discoloration

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.