

ISO-9001 Registered Quality System. ISO-21469 Compliant.

### Sales, Service & Distribution Center

Newark, NJ 07105

Phone: 973-589-9150 Fax: 973-589-4432

Manufacturing, Sales, Service & Distribution Center

Toledo, OH 43605

Phone: 419-691-2491 Fax: 419-693-3806

Sales and Tech Service Support

Phone: 1-800-733-4755

## **PRODUCT DATA**

# LUBRIPLATE SYNXTREME ASAP ANTI-SEIZE ASSEMBLY PASTE

\*NSF International H-1 Registered NSF ISO21469 Certification

## **DESCRIPTION**

LUBRIPLATE SYNXTREME ASAP is our premium anti-seize compound composed of a food grade, high-heat-resistant carrier fortified with rust and corrosion inhibitors and antioxidants. It is designed to lubricate and protect threaded connections and flanges at temperatures to 1,800°F (982°C) and under extreme load pressure conditions.

LUBRIPLATE SYNXTREME ASAP does not separate. It is nondripping, non-hardening, permits easy disassembly and removal of connection even after lengthy service or severe conditions. Stress, strain, and time to disassemble are greatly diminished.

## **ADVANTAGES**

- ⇒ Protects parts from seizing and rusting together
- ⇔ Greatly reduces Maintenance Headaches caused by parts rusting together
- ⇒ Aids in assembly and disassembly of parts
- ⇒ Highly resistant to saltwater corrosion
- ⇔ Compatible with all types of metals/most plastics

# **APPLICATIONS**

LUBRIPLATE SYNXTREME ASAP applications include all Nuts and Bolts, Bushings, Centers, Cam Rollers, Conveyors, Couplings, Dies, Drills and Taps, Fittings, Flanges, Gears and Motors, Keyways, Press Fits, Pumps, Shafts, Sleeves and Slides, Spark Plugs, Valves, and Wristpins

## **CAUTIONS**

Read all information on labels and Safety Data Sheets prior to use. All products should be tested and evaluated for a particular purpose prior to use.

### SERVICE RECOMMENDATIONS

-30°F to 1800°F (-184°C to 982°C)

### SERVICE RECOMMENDATIONS

- ⇒ Products should be stored between 40°F-120°F
- ⇒ Products should be stored in a dry covered environment
- ⇒ Products should not be stored in warm, direct sunlight
- □ Improper storage conditions can significantly alter the shelf life of the product. Such conditions would include temperature, moisture, open containers, etc.

## **TYPICAL TEST DATA\***

PROPERTY	TEST METHOD	TYPICAL RESULTS*
Specific Gravity		1.2
Weight per gallon		10.0 LB
Penetration Range		280 - 400
Oil Separation, 30 hr. at 158°F		1%
Flash Point	ASTM D-92-85	>400°F
Color		White
Friction Coefficient		0.10
Homogeneity		Will not settle, harden or separate under normal conditions
Carrier plus Additive		65%
Solid Lubricants		35%
RoHS		Compliant

### **PACKAGING AVAILABLE**

4/ 8 oz. Brush-Top Cans 1/16 oz. Plastic Tub 40 lb. Pail

\*NSF International H-1 Registration No.

(Meets former USDA 1998 Guidelines)

\*Registered H-1 by NSF International for use in food processing facilities as a lubricant or anti-rust agent on equipment in which there may be incidental contact involving the lubricated part and the edible product.











Part No.

L0404-008

L0404-016

L0404-035

160559

<sup>&</sup>quot;These products are certified OU Kosher Pareve"

<sup>&</sup>quot;These products are Halal certified"