



HEX TAP BOLTS – STEEL ZINC AND 18-8 STAINLESS STEEL

The following Specification Sheet applies to all **Hex Tap Bolts – Steel Zinc and 18-8 Stainless Steel** in our **HTB, JHTB, and JSHTB series**.





	FULLY THREADED HEX TAP BOLTS IFI-199 (2014)							
Nominal or Basic Product Diameter	F Width Across Flats			G Width Across Corners		H Head Height		
	1/4	7/16	0.438	0.425	0.505	0.484	11/64	0.188
5/16	1/2	0.500	0.484	0.577	0.552	7/32	0.235	0.195
3/8	9/16	0.562	0.544	0.650	0.620	1/4	0.268	0.226
7/16	5/8	0.625	0.603	0.722	0.687	19/64	0.316	0.272
1/2	3/4	0.750	0.725	0.866	0.826	11/32	0.364	0.302
5/8	15/16	0.938	0.906	1.083	1.033	27/64	0.444	0.378
3/4	1 1/8	1.125	1.088	1.299	1.240	1/2	0.524	0.455
7/8	1 5/16	1.312	1.269	1.516	1.447	37/64	0.604	0.531
1	1 1/2	1.500	1.450	1.732	1.653	43/64	0.700	0.591

Metallics

229 Cross Street Bristol, CT 06010 www.metallics.us

Phone: 860 589-4186 Toll Free: 800 243-8272 Fax: 860 584-1008 Toll Free Fax: 800 831-9358



Description	ASTM A307 Tap Bolt: A low carbon, hex head bolt with a machined point which is threaded to the head. Grade-5 Tap Bolt: A tap bolt made from medium carbon steel. Grade-8 Tap Bolt: A tap bolt made from medium carbon alloy steel and heat-treated. Stainless Tap Bolt: A tap bolt made from 18-8 stainless steel.					
Applications/ Advantages	ASTM A307 Tap Bolt. To be used in drilled and tapped holes which are threaded full length. Used instead of a stud and a nut. Grade-5 Tap Bolt. Used to mount motors to machinery; also popular in automotive and truck repair. Grade-8 Tap Bolt. Used in automotive and fleet industries where greater tensile strength is required than can be met by a grade-5. Stainless Tap Bolt. Used in in environments corrosive to carbon steel, in tapped holes that are threaded full length.					
Material	ASTM A307 Tap Bolt: Bolts shall be made from a carbon steel which conforms to the following chemical composition requirements— Carbon: 0.33 maximum; Manganese: 0.93; Phosphorous: 0.041 Grade-5 Tap Bolt: AISI 1030 - 1541 or equivalent medium carbon steel. Use of an alloy such as 4037 modified steel is also acceptable. Grade-8 Tap Bolt: Medium carbon alloy steel. Note: For diameters 1/4 thru 7/16 inch, it is permissible to use AISI 1541 steel. Stainless Tap Bolt: 18-8 Stainless steel					
Heat Treatment	Grade-5 Tap Bolt: Bolts shall be heat treated, oil or water quenched, at the option of the manufacturer, and tempered at a minimum tempering temperature of 800°F. Grade-8 Tap Bolt: Bolts shall be heat treated, oil quenched and tempered at a minimum tempering temperature of 800°F.					
Core Hardness	ASTM A307 Tap Bolt: Rockwell B69 - B100 Grade-5 Tap Bolt: Rockwell C25 - C34 Grade-8 Tap Bolt: Rockwell C33 - C39 Stainless Tap Bolt: 1/4 thru 5/8"" diam: Rockwell B95 - C32					
Surface Hardness	Grade-5 Tap Bolt: Rockwell 30N54 maximum Grade-8 Tap Bolt: Rockwell 30N58.6 maximum					
Proof Load	Grade-5 Tap Bolt: 85,000 psi. Grade-8 Tap Bolt: 120,000 psi.					
Yield Strength*	Grade-5 Tap Bolt: 92,000 psi. minimum Grade-8 Tap Bolt: 130,000 psi. minimum Stainless Tap Bolt: 1/4 thru 5/8"" diam: 60,000 psi. minimum					
Tensile Strength	ASTM A307 Tap Bolt: 60,000 psi. minimum Grade-5 Tap Bolt: 120,000 psi. minimum Grade-8 Tap Bolt: 150,000 psi. minimum Stainless Tap Bolt: 1/4 thru 5/8"" diam: 95,000 psi. minimum					
Elongation*	ASTM A307 Tap Bolt: 18% minimum Grade-5 Tap Bolt: 14% minimum Grade-8 Tap Bolt: 12% minimum					
Reduction of Area*	Grades 5 & 8 Tap Bolts: 35% minimum (all sizes)					

Metallics

229 Cross Street Bristol, CT 06010 www.metallics.us

Phone: 860 589-4186 Toll Free: 800 243-8272 Fax: 860 584-1008 Toll Free Fax: 800 831-9358